

Technical Data Sheet

Facestock is topcoated for thermal transfer printing. Resin ribbons are recommended for optimum durability. The topcoat also provides improved ink anchorage for traditional forms of press printing.

Construction

Facestock	50 micron	White PET (TLBPET01)
	50 micron	Matte White PET (TLBPET02)
	50 micron	Matte Silver PET (TLBPET03)
Adhesive	20 micron	acrylic adhesive
Liner	80g	Glassine Liner

Application

- Barcode labels and rating plates.
- Property identification and asset labeling.
- Warning, instruction, and service labels for durable goods.
- Nameplates for durable goods.

Adhesion

Surface	180° peel (N/in)
Stainless steel	14
PC	13
ABS	12

Thermal Transfer Ribbon AXR 7+ 、 T121

Service Temperature Range: -40° C — 150° C

Storage Stability One years stored at 70°F (21°C) and 50% RH